

PRESTO BLACK PC-6

MSDS Number

BBCVD

National Stock Number

6810-00D000501

Product Name

PRESTO BLACK PC-6

Manufacturer

BIRCHWOOD CASEY

Product Identification

Product ID:PRESTO BLACK PC-6

MSDS Date:01/01/1985

FSC:6810

NIIN:00D000501

MSDS Number: BBCVD

Responsible Party

BIRCHWOOD CASEY

Emergency Phone: 612-937-7940

Cage: 0HLC1

Contractor

BIRCHWOOD LABORATORIES, INC.

EDEN PRAIRIE, MN 55344-2138

US

952-937-7931/FAX 952-937-7979

Cage: 0HLC1

Ingredients

SELENIOS ACID (SARA III)

CAS: 7783-00-8

RTECS: VS7175000

Fraction By Weight:

OSHA PEL0.2 MG SE/M3

ACGIH TLV: 0.2 MG SE/M3; 9192

EPA Report Quantity: 10 LBS

DOT Report Quantity: 10 LBS

CU(NO*3)*2

Fraction By Weight:

Hazards

Effects of Overexposure:GASTROINTESTINAL DISTURBANCES,GARLIC ODOR OF BREATH,DIZZINESS,FATIGABILITY,DIFFACULTY BREATHING.

First Aid

First Aid:SKIN OR EYE CONTACT:RINSE AFFECTED AREA IMMEDIATELY AND THOROUGHLY.SEEK MEDICAL ATTENTION FOR EYE CONTACT.

INGESTION:GASTRIC LAVAGE,SALINE CATHARSIS,ADMINISTER OXYGEN IF

BREATHING DIFFICULT.GIVE DIURE TIC,VITAMINS C & B
COMPLEX,METHIONINE SUPPLEMENTS.

Accidental Release

Spill Release Procedures:DILUTE WITH WATER OR NEUTRALIZE WITH SODIUM
BICARBONATE & ABSORB ON SAWDUST OR EQUIVALENT.

Handling

Handling and Storage Precautions:STORE IN ACID RESISTANT
CONTAINERS.AVOID STORING OR TRANSPORTING WITH CYANIDES.

Exposure Controls

Respiratory Protection:NOT NECESSARY WHEN USED ACCORDING TO
INSTRUCTIONS.

Ventilation:LOCAL EXHAUST IS RECOMMENDED.

Protective Gloves:RUBBER OR PLAST

Eye Protection:GOGGLES

Other Protective Equipment:RUBBER OR PLASTIC APRON.

Supplemental Safety and Health

Chemical Properties

HCC:N1

Boiling Pt:B.P. Text:214F

Vapor Pres:UNK

Spec Gravity:1.055

Evaporation Rate & Reference:UNK

Solubility in Water:COMPLETE

Appearance and Odor:ODORLESS BLUE SOLUTION

Percent Volatiles by Volume:0.0

Stability

Stability Indicator/Materials to Avoid:YES

CYANIDES,ORGANIC COMPOUNDS(E.G.OILS,SOLVENTS)

Hazardous Decomposition Products:NO DATA

Disposal

Waste Disposal Methods:ADD 1 OZ,H*2,SO*4 PER GALLON;ADD STEEL WOOL OR
IRON FILINGS(2-4 OZ/GAL):ALLOW TO REACT COMPLETELY;ADJUST PH TO
8.0;FILTER LIQUID TO DRAIN.SOLIDS TO LANDFILL

Disclaimer (provided with this information by the compiling agencies):

This information is formulated for use by elements of the Department
of Defense. The United States of America in no manner whatsoever,
expressly or implied, warrants this information to be accurate and
disclaims all liability for its use. Any person utilizing this
document should seek competent professional advice to verify and
assume responsibility for the suitability of this information to their
particular situation.